

# SPC RIGID CLICK 5.3mm-ACOUSTIC-TITAN CL.

TECHNICAL SPECIFICATIONS	STANDARD	PRODUCT SPECIFICATIONS
Type of Floorcovering	ISO 10582	HETEROGENEOUS PVC
Overall thickness	EN ISO 24346	5.3 mm
Wear layer thickness	EN ISO 23340	0.30 mm
Total weight	EN ISO 23997	7790 g/m <sup>2</sup>
Wear resistance	EN 660-2	Group T
Plank size	EN ISO 24342	228 mm X 1220 mm
Tile size	EN ISO 23342	450 mm X 910 mm
Quantity per box for planks sizes		2,782 m <sup>2</sup>
Quantity per pallet for planks sizes		48 boxes ( 133,54 m <sup>2</sup> )
Quantity per container (20 feet) for planks sizes		20 pallets ( 2670,34 m <sup>2</sup> )
Quantity per box for tiles sizes		2,457 m <sup>2</sup>
Quantity per pallet for tiles sizes		56 boxes ( 137,59 m <sup>2</sup> )
Quantity per container (20 feet) for tiles sizes		20 pallets ( 2751,8 m <sup>2</sup> )
Surface treatment		PUR
Click system		Valinge 2G / Valinge 5Gi
Class of use	EN ISO 10874	23-31

TECHNICAL PERFORMANCES	STANDARD	PRODUCT PERFORMANCES
Fire classification	EN 13501-1	Bfl-s1
Slip resistance	EN 13893	DS
Slip resistance	DIN 51130	R9
Residual indentation	EN ISO 24343-1	≤0,10 mm
Dimensional stability	EN ISO 23999	≤0,15%
Castor chair resistance	ISO 4918	PASS
Furniture leg resistance	EN ISO 16581	PASS
Acoustic insulation	EN ISO 717-2	21 dB
Electrical resistance	EN 1081	<1.0*10 <sup>6</sup> Ω
Underfloor heating compatibility		suitable ( temperature ≤ 27° C)
Electrostatic performances	EN 1815	<2.0kv
Thermal resistance	EN 12667	0,030m <sup>2</sup> .K/W
Light fastness	ISO 105-B02	≥6
Stain resistance	EN ISO 26987	PASS
TVOC after 28 DAYS	ISO 16000	<0.5mg/m <sup>3</sup>
DOP number / CE MARKING	EN 14041/2004	23DOP-SPC 5.3/0.30-003

